


Signature _____

U.S. APPLICATION NO. (If known, see 37 CFR 1.5)		INTERNATIONAL APPLICATION NO.		ATTORNEY'S DOCKET NUMBER	
09/806882		PCT/US99/23146		7292	
				CALCULATIONS PTO USE ONLY	
ENTER APPROPRIATE BASIC FEE AMOUNT =				\$710	
Surcharge of \$130.00 for furnishing the oath or declaration later than [] 20 [] 30 months from the earliest claimed priority date (37 CFR 1.492(e)).				\$0	
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE		
Total Claims	18-20 =	0	x \$18.00	\$0	
Independent Claims	2-3 =	0	x \$80.00	\$0	
MULTIPLE DEPENDENT CLAIM(S) (if applicable)			\$270.00	\$0	
TOTAL OF ABOVE CALCULATIONS =				\$710	
Processing fee of \$130.00 for furnishing the English translation later than [] 20 [] 30 months from the earliest claimed priority date (37 CFR 1.492(f)).				\$0	
TOTAL NATIONAL FEE =				\$710	
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28,3.31). \$40.00 per property +				\$0	
TOTAL FEES ENCLOSED =				\$710	
				Amount to be refunded	\$
				charged	\$
a. [] A check in the amount of \$ _____ to cover the above fees is enclosed.					
b. [x] Please charge my Deposit Account No. <u>16-2480</u> in the amount of \$ <u>710</u> to cover the above fees. A duplicate copy of this sheet is enclosed.					
c. [x] The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. <u>16-2480</u> . A duplicate copy of this sheet is enclosed.					
NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.					
SEND ALL CORRESPONDENCE TO:					
M. Dressman, Patent Attorney Customer Number 27751			 Signature T. David Reed Name <u>32,931</u> Registration Number		

09/806882

I hereby certify that this correspondence is being deposited
with the United States Postal Service as first class mail in an
envelope addressed to, Commissioner of Patent and
Trademarks, Washington, D.C. 20231 on _____

JC02 Rec'd PCT/PTO 05 APR 2001

Name of Attorney

Registration No

Signature of Attorney

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Case 7292

In the Matter of :
US National Phase Entry :
Under 35 USC 371 from :
International Application of :
Panandiker et al., :
Int'l Application No. PCT/US99/23146 : Group Art Unit : N/A
Filed on October 6, 1999 : Examiner : N/A

For Laundry Detergent Compositions with a Combination of Cyclic Amine Based
Polymers and Hydrophobically Modified Carboxy Methyl Cellulose

PRELIMINARY AMENDMENT

The Assistant Commissioner of Patents

Washington, D.C. 20231


Dear Sir:

Before computing the fees for entering the captioned International Application into
the US National Phase, please enter the following amendments.


IN THE CLAIMS:

Please delete current claims 1-10 and replace with the following new set of claims.

1. A detergent composition comprising:
 - a) from 1% to 80% by weight of surfactants selected from the group consisting of nonionic, anionic, cationic, amphoteric zwitterionic surfactants and mixtures thereof; and
 - b) from 0.01%, to 50%, by weight, of a mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers.
2. The detergent composition of claim 1, wherein the hydrophobically modified cellulosic based polymers or oligomers are of the general formula:



wherein each R is selected from the group consisting of R₂, R_C, and




wherein:

- each R₂ is independently selected from the group consisting of H and C₁-C₄ alkyl;

- each R_C is $\text{---}(\text{CH}_2)_y\text{---}\overset{\text{O}}{\parallel}\text{C}\text{---}\text{OZ}$,

wherein each Z is independently selected from the group consisting of M, R₂, R_C, and R_H;

- each R_H is independently selected from the group consisting of C₅-C₂₀ alkyl, C₅-C₇ cycloalkyl, C₇-C₂₀ alkylaryl, C₇-C₂₀ arylalkyl, substituted alkyl, hydroxyalkyl, C₁-C₂₀ alkoxy-2-hydroxyalkyl, C₇-C₂₀ alkylaryloxy-2-hydroxyalkyl, (R₄)₂N-alkyl, (R₄)₂N-2-hydroxyalkyl, (R₄)₃N-alkyl, (R₄)₃N-2-hydroxyalkyl, C₆-C₁₂ aryloxy-2-hydroxyalkyl,



- each R₄ is independently selected from the group consisting of H, C₁-C₂₀ alkyl, C₅-C₇ cycloalkyl, C₇-C₂₀ alkylaryl, C₇-C₂₀ arylalkyl, aminoalkyl, alkylaminoalkyl, dialkylaminoalkyl, piperidinoalkyl, morpholinoalkyl, cycloalkylaminoalkyl and hydroxyalkyl;
- each R₅ is independently selected from the group consisting of H, C₁-C₂₀ alkyl, C₅-C₇ cycloalkyl, C₇-C₂₀ alkylaryl, C₇-C₂₀ arylalkyl, substituted alkyl, hydroxyalkyl, (R₄)₂N-alkyl, and (R₄)₃N-alkyl;

wherein:

M is a suitable cation selected from the group consisting of Na, K, 1/2Ca, and 1/2Mg;


each x is from 0 to 5;

each y is from 1 to 5; and

provided that:

- the Degree of Substitution for group R_H is between 0.0005 and 0.1;
- the Degree of Substitution for group R_C wherein Z is H or M is between 0.2 and 2.0;
- if any R_H bears a positive charge, it is balanced by a suitable anion; and
- two R_4 's on the same nitrogen can together form a ring structure selected from the group consisting of piperidine and morpholine.



3. The detergent composition of claim 1, wherein the cyclic amine based polymers, oligomers or copolymers are of the general formula:




wherein;

each T is independently selected from the group consisting of H, C_1 - C_{12} alkyl, substituted alkyl, C_7 - C_{12} alkylaryl,


$-(CH_2)_hCOOM$, $-(CH_2)_hSO_3M$, $CH_2CH(OH)SO_3M$, $-(CH_2)_hOSO_3M$,




-wherein W comprises at least one cyclic constituent selected from the group consisting of:



in addition to the at least one cyclic constituent, W may also comprise an aliphatic or substituted aliphatic moiety of the general structure;




- each B is independently C₁-C₁₂ alkylene, C₁-C₁₂ substituted alkylene, C₃-C₁₂ alkenylene, C₈-C₁₂ dialkylarylene, C₈-C₁₂ dialkylarylenediyl, and -(R₅O)_nR₅-;
 - each D is independently C₂-C₆ alkylene;
 - each Q is independently selected from the group consisting of hydroxy, C₁-C₁₈ alkoxy, C₂-C₁₈ hydroxyalkoxy, amino, C₁-C₁₈ alkylamino, dialkylamino, trialkylamino groups, heterocyclic monoamino groups and diamino groups;
 - each R₁ is independently selected from the group consisting of H, C₁-C₈ alkyl and C₁-C₈ hydroxyalkyl;
 - each R₂ is independently selected from the group consisting of C₁-C₁₂ alkylene, C₁-C₁₂ alkenylene, -CH₂-CH(OR₁)-CH₂, C₈-C₁₂ alkarylene, C₄-C₁₂ dihydroxyalkylene, poly(C₂-C₄ alkyleneoxy)alkylene, H₂CH(OH)CH₂OR₂OCH₂CH(OH)CH₂-, and C₃-C₁₂ hydrocarbyl moieties;
- provided that when R₂ is a C₃-C₁₂ hydrocarbyl moiety the hydrocarbyl moiety can comprise from about 2 to about 4 branching moieties of the general structure:



- each R₃ is independently selected from the group consisting of H, O, R₂, C₁-C₂₀ hydroxyalkyl, C₁-C₂₀ alkyl, substituted alkyl, C₆-C₁₁ aryl, substituted aryl, C₇-C₁₁ alkylaryl, C₁-C₂₀ aminoalkyl,

$-(CH_2)_hCOOM$, $-(CH_2)_hSO_3M$, $CH_2CH(OH)SO_3M$, $-(CH_2)_hOSO_3M$,



-each R_4 is independently selected from the group consisting of H, C_1 - C_{22} alkyl, C_1 - C_{22} hydroxyalkyl, aryl and C_7 - C_{22} alkylaryl;

-each R_5 is independently selected from the group consisting of C_2 - C_8 alkylene, C_2 - C_8 alkyl substituted alkylene; and

A is a compatible monovalent or di or polyvalent anion;

M is a compatible cation;

b = number necessary to balance the charge;

each x is independently from 3 to 1000;

each c is independently 0 or 1;

each h is independently from 1 to 8;

each q is independently from 0 to 6;


each n is independently from 1 to 20;

each r is independently from 0 to 20; and


each t is independently from 0 to 1.

4. The detergent composition of claim 1, wherein the cyclic amine based polymers, oligomers or copolymers are adducts selected from the group consisting of piperazine, piperadine, epichlorohydrin, epichlorohydrin benzyl quat, epichlorohydrin methyl quat, morpholine and mixtures thereof.


5. The detergent composition of claim 3, wherein each R_1 is H and at least one W is selected from the group consisting of:



6. The detergent composition of claim 3, wherein each R_1 is H and at least one W is selected from the group consisting of:




7. The detergent composition of claim 3, wherein each R_1 is H and at least one W is selected from the group consisting of:



8. The detergent composition of claim 2, wherein each R_H is independently selected from the group consisting of C_5 - C_{20} alkyl, C_5 - C_7 cycloalkyl, C_7 - C_{20} alkylaryl, C_7 - C_{20} arylalkyl, substituted alkyl, hydroxyalkyl, C_1 - C_{20} alkoxy-2-hydroxyalkyl, C_7 - C_{20} alkylaryloxy-2-hydroxyalkyl, $(R_4)_2N$ -

alkyl, (R₄)₂N-2-hydroxyalkyl, (R₄)₃N-alkyl, (R₄)₃N-2-hydroxyalkyl, and C₆-C₁₂ aryloxy-2-hydroxyalkyl.

9. The detergent composition of claim 2, wherein each R_H is independently selected from the



10. The detergent composition of claim 2, wherein the cellulosic based polymer or oligomer has an average molecular weight of from 5,000 to 2,000,000.

11. A laundry additive composition comprising:

- a) from 1% to 80% by weight of water; and
- b) from 0.01% to 5.0%, by weight of a mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers.

12. The laundry additive composition of claim 6, wherein the composition further comprises a pH adjuster and one or more fabric softening components.

13. The detergent composition of claim 1, wherein the composition further comprises a deterative enzyme and an enzyme stabilization system.

14. The detergent composition of claim 1, wherein the composition further comprises an inorganic peroxygen bleaching compound, which is selected from the group consisting of alkali metal salts of perborate, percarbonate and mixtures thereof, and a bleach activator, which is nonanoyloxybenzene sulfonate.

15. The detergent composition of claim 1, wherein the composition further comprises a cellulase enzyme.

16. The detergent composition of claim 14, wherein the composition further comprises a cellulase enzyme.

17. A detergent component in the form of a particle wherein the component comprises a mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers.

18. A detergent component according to claim 17 wherein the particle is an agglomerate and further comprises a carrier material selected from the group consisting of inorganic salts, silicates, aluminosilicates, anionic surfactants, nonionic surfactants and mixtures thereof.

Conclusion

Support for these amendments is found in the claims as originally filed. These amendments are entered to bring the claims into conformance with 37 CFR §1.75; no new matter is added.

Respectfully submitted,

By M. Dressman
Marianne Dressman
Attorney for Applicant(s)
Registration No. 42,498
(513) 627-4132

April 3, 2001
Cincinnati, Ohio
K:/Dressman/PrelAmend/PA7292

**LAUNDRY DETERGENT COMPOSITIONS WITH A COMBINATION OF CYCLIC
AMINE BASED POLYMERS AND HYDROPHOBICALLY MODIFIED CARBOXY
METHYL CELLULOSE**

5

TECHNICAL FIELD

10 The present invention relates to compositions, in either liquid or granular form, for use in laundry applications, wherein the compositions comprise certain cyclic amine based polymer, oligomer or copolymer materials in combination with hydrophobically modified carboxy methyl cellulose. This combination imparts appearance and integrity benefits to fabrics and textiles laundered in washing solutions formed from such compositions.

BACKGROUND OF THE INVENTION

15 It is, of course, well known that alternating cycles of using and laundering fabrics and textiles, such as articles of worn clothing and apparel, will inevitably adversely affect the appearance and integrity of the fabric and textile items so used and laundered. Fabrics and textiles simply wear out over time and with use. Laundering of fabrics and textiles is necessary to remove soils and stains which accumulate therein and thereon during ordinary use. However,
20 the laundering operation itself, over many cycles, can accentuate and contribute to the deterioration of the integrity and the appearance of such fabrics and textiles.

Deterioration of fabric integrity and appearance can manifest itself in several ways. Short fibers are dislodged from woven and knit fabric/textile structures by the mechanical action of laundering. These dislodged fibers may form lint, fuzz or "pills" which are visible on the surface
25 of fabrics and diminish the appearance of newness of the fabric. Further, repeated laundering of fabrics and textiles, especially with bleach-containing laundry products, can remove dye from fabrics and textiles and impart a faded, worn out appearance as a result of diminished color intensity, and in many cases, as a result of changes in hues or shades of color.

Given the foregoing, there is clearly an ongoing need to identify materials which could be
30 added to laundry detergent products that would associate themselves with the fibers of the fabrics and textiles laundered using such detergent products and thereby reduce or minimize the tendency of the laundered fabric/textiles to deteriorate in appearance. Any such detergent product additive material should, of course, be able to benefit fabric appearance and integrity without unduly interfering with the ability of the laundry detergent to perform its fabric cleaning

function. The present invention is directed to the use of a mixture of certain cyclic amine based polymer, oligomer or copolymer materials and hydrophobically modified carboxy methyl cellulose (CMC) in laundry applications that perform in this desired manner.


SUMMARY OF THE INVENTION

The present invention is directed to a detergent composition comprising:

a) from about 1% to about 80% by weight of surfactants selected from the group consisting of nonionic, anionic, cationic, amphoteric zwitterionic surfactants and mixtures thereof; and



b) at least about 0.01%, preferably at least about 0.1%, most preferably at least about 0.5% and less than about 50%, preferably less than about 25.0%, most preferably less than about 5.0%, by weight, of a mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers.

The cyclic amine based polymer, oligomer or copolymer materials which are suitable for use in laundry operations and provide the desired fabric appearance and integrity benefits can be characterized by the following general formula:




wherein:


each T is independently selected from the group consisting of H, C₁-C₁₂ alkyl, substituted alkyl, C₇-C₁₂ alkylaryl, -(CH₂)_hCOOM, -(CH₂)_hSO₃M, CH₂CH(OH)SO₃M, -(CH₂)_hOSO₃M,



-wherein W comprises at least one cyclic constituent selected from the group consisting of:



in addition to the at least one cyclic constituent, W may also comprise an aliphatic or substituted aliphatic moiety of the general structure;



-each B is independently C_1 - C_{12} alkylene, C_1 - C_{12} substituted alkylene, C_3 - C_{12} alkenylene, C_8 - C_{12} dialkylarylene, C_8 - C_{12} dialkylarylenediyl, and $-(\text{R}_5\text{O})_n\text{R}_5$;


-each D is independently C_2 - C_6 alkylene;

-each Q is independently selected from the group consisting of hydroxy, C_1 - C_{18} alkoxy, C_2 - C_{18} hydroxyalkoxy, amino, C_1 - C_{18} alkylamino, dialkylamino, trialkylamino groups, heterocyclic monoamino groups and diamino groups;

-each R_1 is independently selected from the group consisting of H, C_1 - C_8 alkyl and C_1 - C_8 hydroxyalkyl;


-each R_2 is independently selected from the group consisting of C_1 - C_{12} alkylene, C_1 - C_{12} alkenylene, $-\text{CH}_2\text{---CH}(\text{OR}_1)\text{---CH}_2$, C_8 - C_{12} alkarylene, C_4 - C_{12} dihydroxyalkylene, poly(C_2 - C_4 alkyleneoxy)alkylene, $\text{H}_2\text{CH}(\text{OH})\text{CH}_2\text{OR}_2\text{OCH}_2\text{CH}(\text{OH})\text{CH}_2$ -, and C_3 - C_{12} hydrocarbyl moieties;

provided that when R_2 is a C_3 - C_{12} hydrocarbyl moiety the hydrocarbyl moiety can comprise from about 2 to about 4 branching moieties of the general structure:



-each R_3 is independently selected from the group consisting of H, O, R_2 , C_1 - C_{20} hydroxyalkyl, C_1 - C_{20} alkyl, substituted alkyl, C_6 - C_{11} aryl, substituted aryl, C_7 - C_{11} alkylaryl, C_1 - C_{20} aminoalkyl, $-(CH_2)_hCOOM$, $-(CH_2)_hSO_3M$, $CH_2CH(OH)SO_3M$, $-(CH_2)_hOSO_3M$,

5



-each R_4 is independently selected from the group consisting of H, C_1 - C_{22} alkyl, C_1 - C_{22} hydroxyalkyl, aryl and C_7 - C_{22} alkylaryl;

-each R_5 is independently selected from the group consisting of C_2 - C_8 alkylene, C_2 - C_8 alkyl substituted alkylene; and

10

A is a compatible monovalent or di or polyvalent anion;

M is a compatible cation;

b = number necessary to balance the charge;

each x is independently from 3 to about 1000;

15

each c is independently 0 or 1;

each h is independently from about 1 to about 8;

each q is independently from 0 to about 6;


each n is independently from 1 to about 20;

each r is independently from 0 to about 20; and


20

each t is independently from 0 to 1.

Cellulosic based polymer or oligomer materials which are suitable for use in laundry operations and provide the desired fabric appearance and integrity benefits can be characterized by the following general formula:



wherein each R is selected from the group consisting of R₂, R_C, and



wherein:



- 5 - each R₂ is independently selected from the group consisting of H and C₁-C₄ alkyl;

- each R_C is $\text{---}(\text{CH}_2)_y\text{---}\overset{\text{O}}{\parallel}\text{C}\text{---}\text{OZ}$,

wherein each Z is independently selected from the group consisting of M, R₂, R_C, and R_H;

- each R_H is independently selected from the group consisting of C₅-C₂₀ alkyl, C₅-C₇ cycloalkyl, C₇-C₂₀ alkylaryl, C₇-C₂₀ arylalkyl, substituted alkyl, hydroxyalkyl, C₁-C₂₀ alkoxy-2-hydroxyalkyl, C₇-C₂₀ alkylaryloxy-2-hydroxyalkyl, (R₄)₂N-alkyl, (R₄)₂N-2-hydroxyalkyl, (R₄)₃N-alkyl, (R₄)₃N-2-hydroxyalkyl, C₆-C₁₂ aryloxy-2-hydroxyalkyl,

10



- each R₄ is independently selected from the group consisting of H, C₁-C₂₀ alkyl, C₅-C₇ cycloalkyl, C₇-C₂₀ alkylaryl, C₇-C₂₀ arylalkyl, aminoalkyl, alkylaminoalkyl, dialkylaminoalkyl, piperidinoalkyl, morpholinoalkyl, cycloalkylaminoalkyl and hydroxyalkyl;

15

- each R₅ is independently selected from the group consisting of H, C₁-C₂₀ alkyl, C₅-C₇ cycloalkyl, C₇-C₂₀ alkylaryl, C₇-C₂₀ arylalkyl, substituted alkyl, hydroxyalkyl, (R₄)₂N-alkyl, and (R₄)₃N-alkyl;

20

wherein:

M is a suitable cation selected from the group consisting of Na, K, $1/2\text{Ca}$, and $1/2\text{Mg}$;

each x is from 0 to about 5;

each y is from about 1 to about 5; and

5 provided that:

- the Degree of Substitution for group R_H is between about 0.0005 and 0.1, more preferably between about 0.005 and 0.05, and most preferably between about 0.01 and 0.05;

- the Degree of Substitution for group R_C wherein Z is H or M is between about 0.2 and 2.0, more preferably between about 0.3 and 1.0, and most preferably between about 0.4 and
10 0.7;

- if any R_H bears a positive charge, it is balanced by a suitable anion; and

- two R_4 's on the same nitrogen can together form a ring structure selected from the group consisting of piperidine and morpholine.

The cyclic amine based polymer, oligomer or copolymer materials defined above can be
15 used, along with the hydrophobically modified cellulosic based polymers or oligomers, as a washing solution additive in either granular or liquid form. Alternatively, they can be admixed to granular detergents, dissolved in liquid detergent compositions or added to a fabric softening composition.

The ratio of the hydrophobically modified cellulosic to cyclic amine based polymer,
20 oligomer or copolymer materials is within the range of 1000:1 to 1:1000 and is preferably between 100:1 to 50:1, more preferably between 50:1 to 1:1, even more preferably between 10:1 to 1:1.

The laundry detergent compositions herein comprise from about 1% to 80% by weight of
25 a deterative surfactant, from about 0.01% to 80% by weight of an organic or inorganic detergency builder and from about 0.01% to 5% by weight of the mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers based fabric treatment materials of the present invention. The deterative surfactant and detergency builder materials can be any of those useful in conventional laundry detergent products.

30 Aqueous solutions of the mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers of the subject invention comprise from about 0.01% to 80% by weight of the mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers

fabric treatment materials dissolved in water and other ingredients such as stabilizers and pH adjusters.

In its method aspect, the present invention relates to the laundering or treating of fabrics and textiles in aqueous washing or treating solutions formed from effective amounts of the detergent compositions described herein, or formed from the individual components of such compositions. Laundering of fabrics and textiles in such washing solutions, followed by rinsing and drying, imparts fabric appearance benefits to the fabric and textile articles so treated. Such benefits can include improved overall appearance, pill/fuzz reduction, antifading, improved abrasion resistance, and/or enhanced softness. It has been surprisingly determined that the a mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers according to this invention imparts fabric appearance and integrity benefits that are greater than the benefits achieved by a corresponding amount of either component by itself.

DETAILED DESCRIPTION OF THE INVENTION

As noted, when fabric or textiles are laundered in wash solutions which comprise the mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers of the present invention fabric appearance and integrity are enhanced. The mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers can be added to wash solutions by incorporating them into a detergent composition, a fabric softener or by adding them separately to the washing solution. The mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers are described herein primarily as liquid or granular detergent additives but the present invention is not meant to be so limited. The mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers, detergent composition components, optional ingredients for such compositions and methods of using such compositions, are described in detail below. All percentages are by weight unless other specified.

A) Cyclic amine Based Polymer, Oligomer or Copolymer Materials

An essential component of the compositions of the present invention comprises one or more cyclic amine based polymer, oligomer or copolymer. Such materials have been found to impart a number of appearance benefits to fabrics and textiles laundered in aqueous washing solutions formed from detergent compositions which contain a mixture of cyclic amine based

polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers fabric treatment materials. Such fabric appearance benefits can include, for example, improved overall appearance of the laundered fabrics, reduction of the formation of pills and fuzz, protection against color fading, improved abrasion resistance, etc. The cyclic amine based fabric treatment materials used in the compositions and methods herein can provide such fabric appearance benefits with acceptably little or no loss in cleaning performance provided by the laundry detergent compositions into which such materials are incorporated.

The cyclic amine based polymer, oligomer or copolymer component of the compositions herein may comprise combinations of these cyclic amine based materials. For example, a mixture of piperadine and epihalohydrin condensates can be combined with a mixture of morpholine and epihalohydrin condensates to achieve the desired fabric treatment results. Moreover, the molecular weight of cyclic amine based fabric treatment materials can vary within the mixture as is illustrated in the Examples below.

As will be apparent to those skilled in the art, an oligomer is a molecule consisting of only a few monomer units while polymers comprise considerably more monomer units. For the present invention, oligomers are defined as molecules having an average molecular weight below about 1,000 and polymers are molecules having an average molecular weight of greater than about 1,000. Copolymers are polymers or oligomers wherein two or more dissimilar monomers have been simultaneously or sequentially polymerized. Copolymers of the present invention can include, for example, polymers or oligomers polymerized from a mixture of a primary cyclic amine based monomer, e.g., piperadine, and a secondary cyclic amine monomer, e.g., morpholine.

The mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers of the detergent compositions herein will generally comprise from about 0.01% to about 5% by the weight of the detergent composition. More preferably, the mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers will comprise from about 0.1% to about 4% by weight of the detergent compositions, most preferably from about 0.75% to about 3%. However, as discussed above, when used as a washing solution additive, i.e. when mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers is not incorporated into a detergent composition, the concentration of mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers can comprise from about 0.1% to about 80% by weight of the additive material.


Cyclic amine based polymer, oligomer or copolymer materials which are suitable for use in laundry operations and provide the desired fabric appearance and integrity benefits can be characterized by the general formula given in the Summary of the Invention.

Preferred compounds that fall within this general structure include compounds:

5

- wherein each R_1 is H; and

- at least one W is selected from the group consisting of:




10

Even more preferred compounds for the fabric appearance and integrity benefits are those:

- wherein each R_1 is H; and

- at least one W is selected from the group consisting of:


15



And most preferred compounds for the fabric appearance and integrity benefits are those:

-wherein each R_1 is H; and


-at least one W is selected from the group consisting of:



Preferred compounds to be used as the linking group R_2 include, but are not limited to: polyepoxides, ethylenecarbonate, propylenecarbonate, urea, α , β -unsaturated carboxylic acids, esters of α , β -unsaturated carboxylic acids, amides of α , β -unsaturated carboxylic acids, anhydrides of α , β -unsaturated carboxylic acids, di- or polycarboxylic acids, esters of di- or polycarboxylic acids, amides of di- or polycarboxylic acids, anhydrides of di- or polycarboxylic acids, glycidylhalogens, chloroformic esters, chloroacetic esters, derivatives of chloroformic esters, derivatives of chloroacetic esters, epihalohydrins, glycerol dichlorohydrins, bis-(halohydrins), polyetherdihalo-compounds, phosgene, polyhalogens, functionalized glycidyl ethers and mixtures thereof. Moreover, R_2 can also comprise a reaction product formed by reacting one or more of polyetherdiamines, alkylenediamines, polyalkylenepolyamines, alcohols, alkyleneglycols and polyalkyleneglycols with α , β -unsaturated carboxylic acids, esters of α , β -unsaturated carboxylic acids, amides of α , β -unsaturated carboxylic acids and anhydrides of α , β -unsaturated carboxylic acids provided that the reaction products contain at least two double bonds, two carboxylic groups, two amide groups or two ester groups.

Additionally preferred cyclic amine based polymer, oligomer or copolymer materials for use herein include adducts of two or more compositions selected from the group consisting of piperazine, piperadine, epichlorohydrin, epichlorohydrin benzyl quat, epichlorohydrin methyl quat, morpholine and mixtures thereof.

These cyclic amine based polymers can be linear or branched. One specific type of branching can be introduced using a polyfunctional crosslinking agent. An example of such polymer is exemplified below.


[illegible]

	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41	42	43	44	45	46	47	48	49	50	51	52	53	54	55	56	57	58	59	60	61	62	63	64	65	66	67	68	69	70	71	72	73	74	75	76	77	78	79	80	81	82	83	84	85	86	87	88	89	90	91	92	93	94	95	96	97	98	99	100
1	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41	42	43	44	45	46	47	48	49	50	51	52	53	54	55	56	57	58	59	60	61	62	63	64	65	66	67	68	69	70	71	72	73	74	75	76	77	78	79	80	81	82	83	84	85	86	87	88	89	90	91	92	93	94	95	96	97	98	99	100
2	2	1	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41	42	43	44	45	46	47	48	49	50	51	52	53	54	55	56	57	58	59	60	61	62	63	64	65	66	67	68	69	70	71	72	73	74	75	76	77	78	79	80	81	82	83	84	85	86	87	88	89	90	91	92	93	94	95	96	97	98	99	100
3	3	2	1	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41	42	43	44	45	46	47	48	49	50	51	52	53	54	55	56	57	58	59	60	61	62	63	64	65	66	67	68	69	70	71	72	73	74	75	76	77	78	79	80	81	82	83	84	85	86	87	88	89	90	91	92	93	94	95	96	97	98	99	100
4	4	3	2	1	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41	42	43	44	45	46	47	48	49	50	51	52	53	54	55	56	57	58	59	60	61	62	63	64	65	66	67	68	69	70	71	72	73	74	75	76	77	78	79	80	81	82	83	84	85	86	87	88	89	90	91	92	93	94	95	96	97	98	99	100
5	5	4	3	2	1	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41	42	43	44	45	46	47	48	49	50	51	52	53	54	55	56	57	58	59	60	61	62	63	64	65	66	67	68	69	70	71	72	73	74	75	76	77	78	79	80	81																			


[illegible][illegible]

concentration of the cellulosic based component can comprise from about 0.1% to about 80% by weight of the additive material.

One suitable group of cellulosic based polymer or oligomer materials for use herein is characterized by the following formula:




wherein each R is selected from the group consisting of R₂, R_C, and




wherein:

- each R₂ is independently selected from the group consisting of H and C₁-C₄ alkyl;



wherein each Z is independently selected from the group consisting of M, R₂, R_C, and R_H;

- each R_H is independently selected from the group consisting of C₅-C₂₀ alkyl, C₅-C₇ cycloalkyl, C₇-C₂₀ alkylaryl, C₇-C₂₀ arylalkyl, substituted alkyl, hydroxyalkyl, C₁-C₂₀ alkoxy-2-hydroxyalkyl, C₇-C₂₀ alkylaryloxy-2-hydroxyalkyl, (R₄)₂N-alkyl, (R₄)₂N-2-hydroxyalkyl, (R₄)₃N-alkyl, (R₄)₃N-2-hydroxyalkyl, C₆-C₁₂ aryloxy-2-hydroxyalkyl,



- each R₄ is independently selected from the group consisting of H, C₁-C₂₀ alkyl, C₅-C₇ cycloalkyl, C₇-C₂₀ alkylaryl, C₇-C₂₀ arylalkyl, aminoalkyl, alkylaminoalkyl,

dialkylaminoalkyl, piperidinoalkyl, morpholinoalkyl, cycloalkylaminoalkyl and hydroxyalkyl;

- each R_5 is independently selected from the group consisting of H, C_1-C_{20} alkyl, C_5-C_7 cycloalkyl, C_7-C_{20} alkylaryl, C_7-C_{20} arylalkyl, substituted alkyl, hydroxyalkyl, $(R_4)_2N$ -alkyl, and $(R_4)_3N$ -alkyl;

wherein:

M is a suitable cation selected from the group consisting of Na, K, $1/2Ca$, and $1/2Mg$;

each x is from 0 to about 5;

each y is from about 1 to about 5; and

provided that:

- the Degree of Substitution for group R_H is between about 0.0005 and 0.1, more preferably between about 0.005 and 0.05, and most preferably between about 0.01 and 0.05;
- the Degree of Substitution for group R_C wherein Z is H or M is between about 0.2 and 2.0, more preferably between about 0.3 and 1.0, and most preferably between about 0.4 and 0.7;
- if any R_H bears a positive charge, it is balanced by a suitable anion; and
- two R_4 's on the same nitrogen can together form a ring structure selected from the group consisting of piperidine and morpholine.

The "Degree of Substitution" for group R_H , which is sometimes abbreviated herein " DS_{RH} ", means the number of moles of group R_H components that are substituted per anhydrous glucose unit, wherein an anhydrous glucose unit is a six membered ring as shown in the repeating unit of the general structure above.

The "Degree of Substitution" for group R_C , which is sometimes abbreviated herein " DS_{RC} ", means the number of moles of group R_C components, wherein Z is H or M, that are substituted per anhydrous glucose unit, wherein an anhydrous glucose unit is a six membered ring as shown in the repeating unit of the general structure above. The requirement that Z be H or M is necessary to insure that there are a sufficient number of carboxy methyl groups such that the resulting polymer is soluble. It is understood that in addition to the required number of R_C components wherein Z is H or M, there can be, and most preferably are, additional R_C components wherein Z is a group other than H or M.

The production of materials according to the present invention is further defined in the Examples below.

C) Detergent Surfactant

The detergent compositions herein comprise from about 1% to 80% by weight of a detergent surfactant. Preferably such compositions comprise from about 5% to 50% by weight of surfactant. Detergent surfactants utilized can be of the anionic, nonionic, zwitterionic, ampholytic or cationic type or can comprise compatible mixtures of these types. Detergent surfactants useful herein are described in U.S. Patent 3,664,961, Norris, issued May 23, 1972, U.S. Patent 3,919,678, Laughlin et al., issued December 30, 1975, U.S. Patent 4,222,905, Cockrell, issued September 16, 1980, and in U.S. Patent 4,239,659, Murphy, issued December 16, 1980. All of these patents are incorporated herein by reference. Of all the surfactants, anionics and nonionics are preferred.

Useful anionic surfactants can themselves be of several different types. For example, water-soluble salts of the higher fatty acids, i.e., "soaps", are useful anionic surfactants in the compositions herein. This includes alkali metal soaps such as the sodium, potassium, ammonium, and alkylammonium salts of higher fatty acids containing from about 8 to about 24 carbon atoms, and preferably from about 12 to about 18 carbon atoms.

Additional non-soap anionic surfactants which are suitable for use herein include the water-soluble salts, preferably the alkali metal, and ammonium salts, of organic sulfuric reaction products having in their molecular structure an alkyl group containing from about 10 to about 20 carbon atoms and a sulfonic acid or sulfuric acid ester group. (Included in the term "alkyl" is the alkyl portion of acyl groups.) Especially valuable are linear straight chain alkylbenzene sulfonates in which the average number of carbon atoms in the alkyl group is from about 11 to 13, abbreviated as C₁₁₋₁₃ LAS.

Preferred nonionic surfactants are those of the formula R₁(OC₂H₄)_nOH, wherein R₁ is a C₁₀-C₁₆ alkyl group or a C₈-C₁₂ alkyl phenyl group, and n is from 3 to about 80. Particularly preferred are condensation products of C₁₂-C₁₅ alcohols with from about 5 to about 20 moles of ethylene oxide per mole of alcohol, e.g., C₁₂-C₁₃ alcohol condensed with about 6.5 moles of ethylene oxide per mole of alcohol.

Additional suitable surfactants, including polyhydroxy fatty acid amides and amine based surfactants, are disclosed in co-pending PCT Application WO98/14300, Published March 25, 1999, entitled *Laundry Detergent Compositions with Cyclic Amine Based Polymers to Provide Appearance and Integrity Benefits to Fabrics Laundered Therewith*, which was filed on September 15, 1997, in the name of Panandiker et al. The entire disclosure of the Panandiker et al. reference is incorporated herein by reference.

D) Detergent Builder

The detergent compositions herein may also comprise from about 0.1% to 80% by weight of a detergent builder. Preferably such compositions in liquid form will comprise from about 1% to 10% by weight of the builder component. Preferably such compositions in granular form will comprise from about 1% to 50% by weight of the builder component. Detergent builders are well known in the art and can comprise, for example, phosphate salts as well as various organic and inorganic nonphosphorus builders.

Water-soluble, nonphosphorus organic builders useful herein include the various alkali metal, ammonium and substituted ammonium polyacetates, carboxylates, polycarboxylates and polyhydroxy sulfonates. Suitable polycarboxylates for use herein are the polyacetal carboxylates described in U.S. Patent 4,144,226, issued March 13, 1979 to Crutchfield et al., and U.S. Patent 4,246,495, issued March 27, 1979 to Crutchfield et al., both of which are incorporated herein by reference. Particularly preferred polycarboxylate builders are the oxydisuccinates and the ether carboxylate builder compositions comprising a combination of tartrate monosuccinate and tartrate disuccinate described in U.S. Patent 4,663,071, Bush et al., issued May 5, 1987, the disclosure of which is incorporated herein by reference.

Examples of suitable nonphosphorus, inorganic builders include the silicates, aluminosilicates, borates and carbonates. Particularly preferred are sodium and potassium carbonate, bicarbonate, sesquicarbonate, tetraborate decahydrate, and silicates having a weight ratio of SiO_2 to alkali metal oxide of from about 0.5 to about 4.0, preferably from about 1.0 to about 2.4. Also preferred are aluminosilicates including zeolites. Such materials and their use as detergent builders are more fully discussed in Corkill et al., U. S. Patent No. 4,605,509, the disclosure of which is incorporated herein by reference. Also discussed in U. S. Patent No. 4,605,509 are crystalline layered silicates which are suitable for use in the detergent compositions of this invention.

E) Optional Detergent Ingredients

In addition to the surfactants, builders and mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers hereinbefore described, the detergent compositions of the present invention can also include any number of additional optional ingredients. These include conventional detergent composition components such as enzymes and enzyme stabilizing agents, suds boosters or suds suppressers, anti-tarnish and anticorrosion agents, bleaching agents, soil suspending agents, soil release

agents, germicides, pH adjusting agents, non-builder alkalinity sources, chelating agents, organic and inorganic fillers, solvents, hydrotropes, optical brighteners, dyes and perfumes.


A preferred optional ingredients for incorporation into the detergent compositions herein comprises a bleaching agent, e.g., a peroxygen bleach. Such peroxygen bleaching agents may be organic or inorganic in nature. Inorganic peroxygen bleaching agents are frequently utilized in combination with a bleach activator.

Useful organic peroxygen bleaching agents include percarboxylic acid bleaching agents and salts thereof. Suitable examples of this class of agents include magnesium monoperoxyphthalate hexahydrate, the magnesium salt of metachloro perbenzoic acid, 4-nonylamino-4-oxoperoxybutyric acid and diperoxydodecanedioic acid. Such bleaching agents are disclosed in U.S. Patent 4,483,781, Hartman, Issued November 20, 1984; European Patent Application EP-A-133,354, Banks et al., Published February 20, 1985; and U.S. Patent 4,412,934, Chung et al., Issued November 1, 1983. Highly preferred bleaching agents also include 6-nonylamino-6-oxoperoxyhexanoic acid (NAPAA) as described in U.S. Patent 4,634,551, Issued January 6, 1987 to Burns et al.

Inorganic peroxygen bleaching agents may also be used, generally in particulate form, in the detergent compositions herein. Inorganic bleaching agents are in fact preferred. Such inorganic peroxygen compounds include alkali metal perborate and percarbonate materials. For example, sodium perborate (e.g. mono- or tetra-hydrate) can be used. Suitable inorganic bleaching agents can also include sodium or potassium carbonate peroxyhydrate and equivalent "percarbonate" bleaches, sodium pyrophosphate peroxyhydrate, urea peroxyhydrate, and sodium peroxide. Persulfate bleach (e.g., OXONE, manufactured commercially by DuPont) can also be used. Frequently inorganic peroxygen bleaches will be coated with silicate, borate, sulfate or water-soluble surfactants. For example, coated percarbonate particles are available from various commercial sources such as FMC, Solvay Interlox, Tokai Denka and Degussa.

Inorganic peroxygen bleaching agents, e.g., the perborates, the percarbonates, etc., are preferably combined with bleach activators, which lead to the *in situ* production in aqueous solution (i.e., during use of the compositions herein for fabric laundering/bleaching) of the peroxy acid corresponding to the bleach activator. Various non-limiting examples of activators are disclosed in U.S. Patent 4,915,854, Issued April 10, 1990 to Mao et al.; and U.S. Patent 4,412,934 Issued November 1, 1983 to Chung et al. The nonanoyloxybenzene sulfonate (NOBS) and tetraacetyl ethylene diamine (TAED) activators are typical and preferred. Mixtures thereof can also be used. See also the hereinbefore referenced U.S. 4,634,551 for other typical bleaches and activators useful herein.

Other useful amido-derived bleach activators are those of the formulae:



wherein R^1 is an alkyl group containing from about 6 to about 12 carbon atoms, R^2 is an alkylene containing from 1 to about 6 carbon atoms, R^5 is H or alkyl, aryl, or alkaryl containing from about 1 to about 10 carbon atoms, and L is any suitable leaving group. A leaving group is any group that is displaced from the bleach activator as a consequence of the nucleophilic attack on the bleach activator by the perhydrolysis anion. A preferred leaving group is phenol sulfonate.

Preferred examples of bleach activators of the above formulae include (6-octanamido-caproyl)oxybenzenesulfonate, (6-nonanamidocaproyl) oxybenzene-sul-fonate, (6-decanamido-caproyl)oxybenzenesulfonate and mixtures thereof as described in the hereinbefore referenced U.S. Patent 4,634,551.

Another class of useful bleach activators comprises the benzoxazin-type activators disclosed by Hodge et al. in U.S. Patent 4,966, 723, Issued October 30, 1990, incorporated herein by reference. See also U.S. Patent 4,545,784, Issued to Sanderson, October 8, 1985, incorporated herein by reference, which discloses acyl caprolactams, including benzoyl caprolactam, adsorbed into sodium perborate.

If utilized, peroxygen bleaching agent will generally comprise from about 2% to 30% by weight of the detergent compositions herein. More preferably, peroxygen bleaching agent will comprise from about 2% to 20% by weight of the compositions. Most preferably, peroxygen bleaching agent will be present to the extent of from about 3% to 15% by weight of the compositions herein. If utilized, bleach activators can comprise from about 2% to 10% by weight of the detergent compositions herein. Frequently, activators are employed such that the molar ratio of bleaching agent to activator ranges from about 1:1 to 10:1, more preferably from about 1.5:1 to 5:1.

Additional suitable bleaching agents and bleach activators are disclosed in co-pending PCT Application WO98/14300, Published March 25, 1999, entitled *Laundry Detergent Compositions with Cyclic Amine Based Polymers to Provide Appearance and Integrity Benefits to Fabrics Laundered Therewith*, which was filed on September 15, 1997, in the name of Panandiker et al. The entire disclosure of the Panandiker et al. reference was incorporated by reference above.

Another highly preferred optional ingredient in the detergent compositions herein is a deterative enzyme component. Enzymes can be included in the present detergent compositions for a variety of purposes, including removal of protein-based, carbohydrate-based, or triglyceride-based stains from substrates, for the prevention of refugee dye transfer in fabric

laundrying, and for fabric restoration. Suitable enzymes include proteases, amylases, lipases, cellulases, peroxidases, and mixtures thereof of any suitable origin, such as vegetable, animal, bacterial, fungal and yeast origin. Preferred selections are influenced by factors such as pH-activity and/or stability, optimal thermostability, and stability to active detergents, builders and the like. In this respect bacterial or fungal enzymes are preferred, such as bacterial amylases and proteases, and fungal cellulases.

"Detergent enzyme", as used herein, means any enzyme having a cleaning, stain removing or otherwise beneficial effect in a laundry detergent composition. Preferred enzymes for laundry purposes include, but are not limited to, proteases, cellulases, lipases, amylases and peroxidases.

Enzymes are normally incorporated into detergent compositions at levels sufficient to provide a "cleaning-effective amount". The term "cleaning-effective amount" refers to any amount capable of producing a cleaning, stain removal, soil removal, whitening, deodorizing, or freshness improving effect on substrates such as fabrics. In practical terms for current commercial preparations, typical amounts are up to about 5 mg by weight, more typically 0.01 mg to 3 mg, of active enzyme per gram of the detergent composition. Stated otherwise, the compositions herein will typically comprise from 0.001% to 5%, preferably 0.01%-1% by weight of a commercial enzyme preparation. Protease enzymes are usually present in such commercial preparations at levels sufficient to provide from 0.005 to 0.1 Anson units (AU) of activity per gram of composition. Higher active levels may be desirable in highly concentrated detergent formulations.


Cellulases usable herein include those disclosed in U.S. Patent No. 4,435,307, Barbesgaard et al., March 6, 1984, and GB-A-2.075.028; GB-A-2.095.275 and DE-OS-2.247.832. CAREZYME® and CELLUZYME® (Novo) are especially useful. See also WO 9117243 to Novo.

The enzyme-containing compositions herein may optionally also comprise from about 0.001% to about 10%, preferably from about 0.005% to about 8%, most preferably from about 0.01% to about 6%, by weight of an enzyme stabilizing system. The enzyme stabilizing system can be any stabilizing system which is compatible with the detergent enzyme. Such a system may be inherently provided by other formulation actives, or be added separately, e.g., by the formulator or by a manufacturer of detergent-ready enzymes. Such stabilizing systems can, for example, comprise calcium ion, boric acid, propylene glycol, short chain carboxylic acids, boronic acids, and mixtures thereof, and are designed to address different stabilization problems depending on the type and physical form of the detergent composition.

The compositions of the present invention may also include dye transfer inhibiting agents such as polyvinyl pyrrolidone polymers, polyamine N-oxide polymers, copolymers of N-vinylpyrrolidone and N-vinylimidazole, manganese phthalocyanine, peroxidases, and mixtures thereof. These agents typically comprise from about 0.01% to about 10% by weight of the composition, preferably from about 0.01% to about 5%, and more preferably from about 0.05% to about 2%.

More specifically, the polyamine N-oxide polymers preferred for use herein contain units having the following structural formula: $R-A_x-P$; wherein P is a polymerizable unit to which an N-O group can be attached or the N-O group can form part of the polymerizable unit or the N-O group can be attached to both units; A is one of the following structures: -NC(O)-, -C(O)O-, -S-, -O-, -N=; x is 0 or 1; and R is aliphatic, ethoxylated aliphatics, aromatics, heterocyclic or alicyclic groups or any combination thereof to which the nitrogen of the N-O group can be attached or the N-O group is part of these groups. Preferred polyamine N-oxides are those wherein R is a heterocyclic group such as pyridine, pyrrole, imidazole, pyrrolidine, piperidine and derivatives thereof.

The N-O group can be represented by the following general structures:



wherein R_1 , R_2 , R_3 are aliphatic, aromatic, heterocyclic or alicyclic groups or combinations thereof; x, y and z are 0 or 1; and the nitrogen of the N-O group can be attached or form part of any of the aforementioned groups. The amine oxide unit of the polyamine N-oxides has a $pK_a < 10$, preferably $pK_a < 7$, more preferred $pK_a < 6$.

Any polymer backbone can be used as long as the amine oxide polymer formed is water-soluble and has dye transfer inhibiting properties. Examples of suitable polymeric backbones are polyvinyls, polyalkylenes, polyesters, polyethers, polyamide, polyimides, polyacrylates and mixtures thereof. These polymers include random or block copolymers where one monomer type is an amine N-oxide and the other monomer type is an N-oxide. The amine N-oxide polymers typically have a ratio of amine to the amine N-oxide of 10:1 to 1:1,000,000. However, the number of amine oxide groups present in the polyamine oxide polymer can be varied by appropriate copolymerization or by an appropriate degree of N-oxidation. The polyamine oxides can be obtained in almost any degree of polymerization.

Typically, the average molecular weight is within the range of 500 to 1,000,000; more preferred 1,000 to 500,000; most preferred 5,000 to 100,000.

The most preferred polyamine N-oxide useful in the detergent compositions herein is poly(4-vinylpyridine-N-oxide) which as an average molecular weight of about 50,000 and an amine to amine N-oxide ratio of about 1:4. This preferred class of materials can be referred to as "PVNO".

Further suitable dye transfer inhibitors can be found in U. S. Pat. No. 5,466,802, issued Nov. 14, 1995 to Panandiker et al., which is hereby incorporated by reference.

F) Detergent Composition Preparation

The detergent compositions according to the present invention can be in liquid, paste or granular form. Such compositions can be prepared by combining the essential and optional components in the requisite concentrations in any suitable order and by any conventional means. The forgoing description of uses for the mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers defined herein are intended to be exemplary and other uses will be apparent to those skilled in the art and are intended to be within the scope of the present invention.

Granular compositions, for example, are generally made by combining base granule ingredients, e.g., surfactants, builders, water, etc., as a slurry, and spray drying the resulting slurry to a low level of residual moisture (5-12%). The remaining dry ingredients, e.g., granules of the essential mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers, can be admixed in granular powder form with the spray dried granules in a rotary mixing drum. The liquid ingredients, e.g., solutions of the essential mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers, enzymes, binders and perfumes, can be sprayed onto the resulting granules to form the finished detergent composition. Granular compositions according to the present invention can also be in "compact form", i.e. they may have a relatively higher density than conventional granular detergents, i.e. from 550 to 950 g/l. In such case, the granular detergent compositions according to the present invention will contain a lower amount of "inorganic filler salt", compared to conventional granular detergents; typical filler salts are alkaline earth metal salts of sulphates and chlorides, typically sodium sulphate; "compact" detergents typically comprise not more than 10% filler salt.

Liquid detergent compositions can be prepared by admixing the essential and optional ingredients thereof in any desired order to provide compositions containing components in the requisite concentrations. Liquid compositions according to the present invention can also be in

"compact form", in such case, the liquid detergent compositions according to the present invention will contain a lower amount of water, compared to conventional liquid detergents. Addition of the mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers to liquid detergent or other aqueous compositions of this invention may be accomplished by simply mixing into the liquid solutions the desired mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers.

The methods and compositions heretofore disclosed may also be applied towards the production of particles that may be used as one of the component detergent granules in a granular detergent composition.

4096392 0400 4096392

G) Fabric Laundering Method

The present invention also provides a method for laundering fabrics in a manner which imparts fabric appearance benefits provided by the mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers used herein. Such a method employs contacting these fabrics with an aqueous washing solution formed from an effective amount of the detergent compositions hereinbefore described or formed from the individual components of such compositions. Contacting of fabrics with washing solution will generally occur under conditions of agitation although the compositions of the present invention may also be used to form aqueous unagitated soaking solutions for fabric cleaning and treatment.

Agitation is preferably provided in a washing machine for good cleaning. Washing is preferably followed by drying the wet fabric in a conventional clothes dryer. An effective amount of a high density liquid or granular detergent composition in the aqueous wash solution in the washing machine is preferably from about 500 to about 7000 ppm, more preferably from about 1000 to about 3000 ppm.

H) Fabric Conditioning and Softening

The mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers hereinbefore described as components of the laundry detergent compositions herein may also be used to treat and condition fabrics and textiles in the absence of the surfactant and builder components of the detergent composition embodiments of this invention. Thus, for example, a fabric conditioning composition comprising only the mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers themselves, or comprising an aqueous solution of the mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers, may be added during the rinse cycle of a conventional home laundering operation in order to impart the desired fabric appearance and integrity benefits hereinbefore described.

Additional suitable fabric softening agents are disclosed in co-pending PCT Application WO98/14300, Published March 25, 1999, entitled *Laundry Detergent Compositions with Cyclic Amine Based Polymers to Provide Appearance and Integrity Benefits to Fabrics Laundered Therewith*, which was filed on September 15, 1997, in the name of Panandiker et al. The entire disclosure of the Panandiker et al. reference was incorporated by reference above

The compositions of the present invention comprise at least about 1%, preferably from about 10%, more preferably from about 20% to about 80%, more preferably to about 60% by weight, of the composition of one or more fabric softener actives.

5

EXAMPLES

The following examples illustrate the compositions and methods of the present invention, but are not necessarily meant to limit or otherwise define the scope of the invention.

EXAMPLE 1

10 **Synthesis of the adduct of imidazole and epichlorohydrin (Ratio of imidazole:epichlorohydrin 1:1):**

The polycationic condensate is prepared by reacting imidazole and epichlorohydrin. To a round bottomed flask equipped with a magnetic stirrer, condenser and a thermometer are added imidazole (0.68 moles) and 95 mL water. The solution is heated to 50°C followed by dropwise addition of epichlorohydrin (0.68 moles). After all the epichlorohydrin is added, the temperature is raised to 80°C until all the alkylating agent is consumed. The condensate produced had molecular weight of about 12,500.

EXAMPLE 2

20 **Synthesis of the adduct of imidazole and epichlorohydrin (Ratio of imidazole:epichlorohydrin 1.4:1)**

To a round bottomed flask equipped with a magnetic stirrer, condenser and a thermometer are added imidazole (0.68 moles) and 95 mL water. The solution is heated to 50°C followed by dropwise addition of epichlorohydrin (0.50 moles). After all the epichlorohydrin is added, the temperature is raised to 80°C until all the alkylating agent is consumed. The condensate produced had molecular weight of about 2000.

EXAMPLE 3

30 **Synthesis of the adduct of piperazine, morpholine and epichlorohydrin (Ratio 1.8/0.8/2.0)**

Into a round bottom flask equipped with stirrer, thermometer, dropping funnel and reflux condenser 154.8 g (1.8 mole) of piperazine and 69.6 g (0.8 mole) of morpholine and 220 ml of water are added. After a clear solution at 40°C is obtained, the solution is heated to 55-65°C and with vigorous stirring 185 g (2 mole) of epichlorohydrin is added at such a rate, that the temperature does not exceed 80°C. After all the epichlorohydrin is added the reaction mixture is

heated to 85°C until all of the alkylating agents is consumed (negative Preussmann test after 4 hours). 108.8 g (0.68 mole) of 25% NaOH and 40 g of water are added and the reaction mixture is stirred for another hour at 85°C. Then an additional 47 g of water is added and the mixture is allowed to cool to room temperature.

5

EXAMPLE 4

Synthesis of the adduct of piperazine/morpholine/epi, in a ratio of 1.8/0.8/2.0

Into a round bottom flask equipped with stirrer, thermometer, dropping funnel and reflux condenser 154.8 g (1.8 mole) of piperazine and 69.6 g (0.8 mole) of morpholine and 220 ml of water are added. After a clear solution at 40°C is obtained, the solution is heated to 55-65°C and with vigorous stirring 185 g (2 mole) of epichlorohydrin is added at such a rate, that the temperature does not exceed 80°C. After all the epichlorohydrin is added the reaction mixture is heated to 85°C until all of the alkylating agents has been consumed (negative Preussmann test after 4 hours). 108.8 g (0.68 mole) of 25% NaOH and 40 g of water is added and the reaction mixture is stirred for another hour at 85°C. Then an additional 47 g of water are added and the mixture is allowed to cool to room temperature.

10

15

EXAMPLE 5

Adduct of piperazine/morpholine/epi from Example 4, 100% oxidized

233.6 g (equivalent to 1,292 mole oxidizable nitrogen atoms) of the material from Example 4 above is mixed with 22.1 g (0.276) of 50% NaOH and then heated to 55-65°C. At that temperature 102.4 g (1,421 mole) of H₂O₂ (47.2%) is added dropwise over a period of 3.5 hours. After the addition is complete, the reaction mixture is held at the same temperature for 3 more hours and is then stirred at room temperature overnight. Pt/C was added, unreacted H₂O₂ destroyed and the solution then filtered.

20

25

The reaction product is characterized as follows:

water content	58%
pH	5.6
chloride content	1.593 mmole/g

30

EXAMPLE 6

Synthesis of the adduct of imidazole/piperazine/epi, in a ratio 1.0/3.0/4.0

68.8g (1.0 mole) of imidazole and 260.6 g (3.0 mole) of piperazine are dissolved in 700.2 g of water and at a temperature of 50-60°C, 370 g (4.0 mole) of epichlorhydrin is added dropwise. After the addition is complete, the reaction mixture is stirred for additional 5 hours at 80°C.

5

EXAMPLE 7

Adduct of imidazole/piperazine/epi from Example 6, 100% oxidized

To 237 g of the product from Example 6 above (equivalent to 1,022 mole of oxidizable nitrogen atoms) 80.7 g (1.12 mole) of a 47.2% solution of H₂O₂ in water is added over a period of 5 hours at 40°C. After that, the mixture is heated to 50-60°C until the theoretical amount of H₂O₂ has been consumed. Unreacted H₂O₂ is destroyed by using Pt/C and the solution is then filtered.

The reaction product is characterized as follows:

water content:	58.6%
15 pH:	2.86
chloride content:	3.694 mmole/g
Mn (GPC):	340
Mw (GPC):	940
Mn/Mw:	2.8+/-0.1

20

EXAMPLE 8

Synthesis of hydrophobically modified CMC Materials

The carboxylation of cellulose to produce CMC is a procedure that is well known to those skilled in the art. One method of producing the modified CMC materials of this invention, is to add during the CMC making process the material, or materials, to be substituted. An example of such as procedure is given below. This same procedure can be utilized with the other substituent materials described herein by replacing the hexylchloride with the substituent material, or materials, of interest, for example, cetylchloride. The amount of material that should be added to the CMC making process to achieve the desired degree of substitution will be easily calculated by those skilled in the art in light of the following Examples.

30

EXAMPLE 9

Synthesis of Hexylether of CMC

This example illustrates the preparation of a hydrophobically modified carboxymethyl cellulose and is representative of preparation of all of the cellulose ether derivatives of this invention.

Cellulose (20 g), sodium hydroxide (10 g), water (30 g), and ethanol (150 g) are charged into a 500 ml glass reactor. The resulting alkali cellulose is stirred 45 minutes at 25°C. Then monochloroacetic acid (15 g) and hexylchloride (1 g) are added and the temperature raised over time to 95°C and held at 95°C for 150 minutes. The reaction is cooled to 70°C, and then cooled to 25°C. Neutralization is accomplished by the addition of a sufficient amount of nitric acid/acetic acid to achieve a slurry pH of between 8 and 9. The slurry is filtered to obtain a hexylether of CMC.

EXAMPLE 10

Cellulosic Polymers Used in Test Detergent Compositions

Representative modified cellulosic polymers for use in the liquid and granular detergent compositions described below are characterized in Tables 10 A and 10 B. The General Polymer Parameters are common to all of the polymers, while the specific chemical structure of the materials tested are listed under the Specific Polymer Parameters.

Table 10 A

General Polymer Parameters

Molecular Parameters	Description
Polymer Backbone	Carboxymethylcellulose
Degree of Carboxymethylation	$DS_{RC} = 0.3 - 2.0$; preferred $DS_{RC} = 0.5 - 0.70$.
Distribution of Carboxymethyls	Even and random distribution of carboxylmethyls along the backbone
Molecular Weight	Mw: 5,000 - 2,000,000. Preferred: medium (approx 250,000 g/mol)
Type of Modification	Ether modification (in addition to carboxymethylation). Mixed cellulose ether
Level of Modification	$DS_{RH} =$ about 0.001 to about 0.1

Table 10 B
Table Specific Polymer Parameters

ID	Polymer	Type of Modification***	Types of Chemistry
*A	Hexyl CMC	Hexyl ether	Chlorohexane added to CMC making process
*B	Decyl CMC	Decyl ether	Chlorodecane added to CMC making process
**C	C12-C13 alkoxy-2-hydroxypropyl CMC	C12-C13 alkoxy-2-hydroxypropyl ether	C12-C13 alkyl glycidyl ether added to CMC making process
*D	Hexadecyl CMC	Hexadecyl ether	Chlorohexadecane added to CMC making process
*E	Chloride salt of 3-trimethylammonio-2-hydroxypropyl ether of CMC	chloride salt of 3-trimethylammonio-2-hydroxypropyl ether	2,3-epoxypropyltrimethyl ammonium chloride added to the CMC making process
*F	[-(C(O)-CH(C16H33)-C(O)CH2(C16H33)] ester of CMC or 1,3-dioxo-2-hexadecyloctadecyl ester of CMC		Cetyl Ketene Dimer added to CMC making process.

CMC = Carboxymethylcellulose

5 * Manufactured by Metsa Specialty Chemicals


** Manufactured by Akzo








***DS_{RH} for these materials was in the range of from about 0.001 to about 0.1








EXAMPLE 11









10 The following are idealized chemical structures for certain cyclic amine based polymers, oligomers or copolymers of this invention. Side reactions expected to occur during the condensation are not shown.










Table 11









Example	Material
1	<p>Adduct of Imidazole-epichlorohydrin (Ratio of imidazole:epichlorohydrin 1:1, Polymer from Example 1)</p>  <p>(Idealized Structure)</p>

2	<p>Adduct of Imidazole-epichlorohydrin (Ratio of imidazole:epichlorohydrin 1.36:1, Polymer from Example 2)</p>  <p>(Idealized Structure)</p>
3	<p>Adduct of Imidazole-epichlorohydrin (Ratio of imidazole:epichlorohydrin 1.75:1)</p>  <p>(Idealized Structure)</p>
4	<p>Adduct of Imidazole-epichlorohydrin-trisglycidyl ether from glycerine (Ratio of imidazole:epichlorohydrin: trisglycidylether 2.0:1.76:0.26)</p>  <p>Idealized Structure</p>
5	<p>Adduct of Imidazole-epichlorohydrin- -trisglycidyl ether from glycerine(Ratio of imidazole:epichlorohydrin: -trisglycidyl ether from glycerine 2.0:1.9:0.1)</p> 
6	<p>Adduct of piperazine and epichlorohydrin (ratio 1:1)</p> 
7	<p>Adduct of piperazine and epichlorohydrin (ratio 1:1), benzyl quat</p> 
8	<p>Adduct of piperazine and epichlorohydrin (ratio 1:1) methyl quat</p> 

9	Adduct of piperazine, morpholine and epichlorohydrin (ratio 0.9:0.4:1.0) 
10	Adduct of piperazine, piperidine and epichlorohydrin (ratio 0.9:0.4:1.0) 
11	Adduct of piperazine, morpholine and epichlorohydrin (ratio 0.9:0.4:1.0) methyl quat 
12	Adduct of piperazine, piperidine and epichlorohydrin (ratio 0.9:0.4:1.0) methyl quat 
13	Adduct of piperazine, morpholine and epichlorohydrin (ratio 0.9:0.4:1.0) benzyl quat 
14	Adduct of piperazine, piperidine and epichlorohydrin (ratio 0.9:0.4:1.0) benzyl quat 
15	Adduct of imidazole, piperazine and epichlorohydrin (ratio 2:1:3) 


16	Adduct of imidazole, piperazine and epichlorohydrin (ratio 1:1:2) 
17	Adduct of imidazole, 1,6 diaminoheptane and epichlorohydrin (ratio 1:1:2) 
18	Adduct of imidazole, dimethylaminopropylamine and epichlorohydrin (ratio 1.02:0.34:1.0) 
19	Adduct of imidazole-epichlorohydrin and chloroacetic acid (Ratio- 1.36:0.97:0.07) 
20	Adduct of imidazole-epichlorohydrin and chloroacetic acid (Ratio- 1.36:0.93:0.14) 
21	Adduct of imidazole-epichlorohydrin and chloroacetic acid (Ratio- 1.36:0.83:0.34) 
22	Adduct of imidazole-epichlorohydrin and 3-chlorohydroxypropyl sulfonic acid (ratio: 1.0:0.83:0.34) 
23	Adduct of imidazole-epichlorohydrin and 3-chlorohydroxypropyl sulfonic acid (ratio:1.0:0.75:0.5) 

24	Adduct of imidazole, piperazine and epichlorohydrin (Ratio- 1.0:1.0:2.0) quat with 0.22 moles of chloroacetate 
25	Adduct of imidazole, piperazine and epichlorohydrin (Ratio- 1.0:3.0:4.0) quat with 0.32 moles of chloroacetate 
26	Adduct of imidazole, piperazine and epichlorohydrin (Ratio- 1.0:1.0:2.0) quat with 0.45 moles of chloroacetate 
27	Adduct of imidazole and epichlorohydrin, (ratio 1.75:1) oxidized 
28	Adduct of piperazine and epichlorohydrin (ratio 1:1) 100% oxidized 
29	Adduct of piperazine and epichlorohydrin (ratio 1:1) 50% oxidized 
30	Adduct of piperazine, morpholine and epichlorohydrin (ratio 1:0.2:1) 100% oxidized 
31	Adduct of piperazine, morpholine and epichlorohydrin (ratio 1:0.2:1) 25% methyl quat and oxidized 
32	Adduct of imidazole, piperazine and epichlorohydrin (ratio 1:3:4) 100% oxidized 

33	Adduct of imidazole, piperazine and epichlorohydrin (ration 1:3:4) 50% oxidized 
34	Adduct of imidazole, piperazine and epichlorohydrin (ration 1:1:2) 100% oxidized 
35	Adduct of imidazole, piperazine and epichlorohydrin (ration 1:5:6) 100% oxidized 
36	Adduct of imidazole, piperazine and epichlorohydrin (ration 1:10:11) 100% oxidized 
37	Adduct of imidazole, piperazine and epichlorohydrin (Ratio-1.0:3.0:4.0) quat with 0.32 moles of chloroacetate and oxidized 
38	Adduct of imidazole, piperazine and epichlorohydrin (Ratio-1.0:1.0:2.0) quat with 0.45 moles of chloroacetate and oxidized 
39	Adduct of imidazole, piperazine and epichlorohydrin (Ratio-1.0:5.0:6.0) quat with 0.32 moles of chloroacetate and oxidized 
40	Adduct of imidazole, piperazine and epichlorohydrin (Ratio-1.0:1.0:2.0) quat with 0.45 moles of dimethyl sulfate and oxidized 

41

Adduct of imidazole, dimethylaminopropylamine and
epichlorohydrin (ratio 1.02:0.34:1.0) oxidized



EXAMPLE 12**Granular Detergent Test Composition Preparation**

Several heavy duty granular detergent compositions are prepared containing a mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers. These granular detergent compositions all have the following basic formula:

Table 12

Component	Wt. %
C₁₂ Linear alkyl benzene sulfonate	9.31
C₁₄₋₁₅ alkyl ether (0.35 EO) sulfate	12.74
Zeolite Builder	27.79
Sodium Carbonate	27.31
PEG 4000	1.60
Dispersant	2.26
C₁₂₋₁₃ Alcohol Ethoxylate (9 EO)	1.5
Sodium Perborate	1.03
Soil Release Polymer	0.41
Enzymes	0.59
Cyclic Amine Based Polymers or Oligomers	3.0
Hydrophobically Modified Cellulosic Based Polymers or Oligomers	1.0
Perfume, Brightener, Suds Suppressor, Other Minors, Moisture, Sulfate	<u>Balance</u>
	100%

EXAMPLE 13**Liquid Detergent Test Composition Preparation**

Several heavy duty liquid detergent compositions are prepared a mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers. These liquid detergent compositions all have the following basic formula:

Table 13

Component	Wt. %
C₁₂₋₁₅ alkyl ether (2.5) sulfate	38
C₁₂ glucose amide	6.86
Citric Acid	4.75
C₁₂₋₁₄ Fatty Acid	2.00
Enzymes	1.02
MEA	1.0
Propanediol	0.36
Borax	6.58
Dispersant	1.48
Na Toluene Sulfonate	6.25

Cyclic Amine Based Polymers or Oligomers	1.0
Hydrophobically Modified Cellulosic Based Polymers or Oligomers	0.1
Dye, Perfume, Brighteners, Preservatives, Suds Suppressors, Other Minors, Water	<u>Balance</u>
	100%

EXAMPLE 14**Granular Detergent Test Composition Preparation**

Several granular detergent compositions are prepared containing a mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers. Such granular detergent compositions all have the following basic formula:

Table 14

	Example	Comparative
Component	Wt. %	Wt%
Na C₁₂ Linear alkyl benzene sulfonate	9.40	9.40
Na C₁₄₋₁₅ alkyl sulfonate	11.26	11.26
Zeolite Builder	27.79	27.79
Sodium Carbonate	27.31	27.31
PEG 4000	1.60	1.60
Dispersant, Na polyacrylate	2.26	2.26
C₁₂₋₁₃ alkyl ethoxylate (E9)	1.5	1.5
Sodium Perborate	1.03	1.03
Cyclic Amine Based Polymers or Oligomers	0.8	0
Hydrophobically Modified Cellulosic Based Polymers or Oligomers	0.3	0
Other Adjunct ingredients	<u>Balance</u>	<u>Balance</u>
	100%	100%

EXAMPLE 15


A detergent agglomerate which may be used as a particulate component in a detergent composition is prepared according to the following formulas and ranges. The granule may be manufactured by agglomeration methods known to those skilled in the art; some of which are described in the present application.

	<u>Ex. 15A</u>	<u>Ex. 15B</u>
<u>Component</u>	Wt %	Wt %
Cyclic Amine Based Polymers or Oligomers	2-7	8-10
Hydrophobically Modified Cellulosic Based Polymers or Oligomers	20-70	80-90
Zeolite Builder	0-70	0
Dispersant/Binder¹	2-6	0
Water and Misc.	<u>Balance</u>	<u>Balance</u>
	100%	100%


1: Dispersant is Na Polyacrylate 4500, Polyethylene Glycol or a mixture of both.

WHAT IS CLAIMED IS:

1. A detergent composition characterized by:
 - a) from 1% to 80% by weight of surfactants selected from the group consisting of nonionic, anionic, cationic, amphoteric zwitterionic surfactants and mixtures thereof; and
 - b) at least 0.01%, preferably at least 0.1%, most preferably at least 0.5% and no more than 50%, preferably no more than 25.0%, most preferably no more than 5.0%, by weight, of a mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers.
2. The detergent composition of claim 1, wherein the hydrophobically modified cellulosic based polymers or oligomers are of the general formula:



wherein each R is selected from the group consisting of R_2 , R_C , and



wherein:


- each R_2 is independently selected from the group consisting of H and C_1 - C_4 alkyl;

- each R_C is $\text{---}(\text{CH}_2)_y\text{---}\overset{\text{O}}{\parallel}\text{C}\text{---}\text{OZ}$,

wherein each Z is independently selected from the group consisting of M, R_2 , R_C , and R_H ;

- each R_H is independently selected from the group consisting of C_5 - C_{20} alkyl, C_5 - C_7 cycloalkyl, C_7 - C_{20} alkylaryl, C_7 - C_{20} arylalkyl, substituted alkyl, hydroxyalkyl, C_1 - C_{20}

alkoxy-2-hydroxyalkyl, C₇-C₂₀ alkylaryloxy-2-hydroxyalkyl, (R₄)₂N-alkyl, (R₄)₂N-2-hydroxyalkyl, (R₄)₃N-alkyl, (R₄)₃N-2-hydroxyalkyl, C₆-C₁₂ aryloxy-2-hydroxyalkyl,



- each R₄ is independently selected from the group consisting of H, C₁-C₂₀ alkyl, C₅-C₇ cycloalkyl, C₇-C₂₀ alkylaryl, C₇-C₂₀ arylalkyl, aminoalkyl, alkylaminoalkyl, dialkylaminoalkyl, piperidinoalkyl, morpholinoalkyl, cycloalkylaminoalkyl and hydroxyalkyl;
- each R₅ is independently selected from the group consisting of H, C₁-C₂₀ alkyl, C₅-C₇ cycloalkyl, C₇-C₂₀ alkylaryl, C₇-C₂₀ arylalkyl, substituted alkyl, hydroxyalkyl, (R₄)₂N-alkyl, and (R₄)₃N-alkyl;

wherein:

M is a suitable cation selected from the group consisting of Na, K, 1/2Ca, and 1/2Mg;


each x is from 0 to 5;

each y is from 1 to 5; and

provided that:

- the Degree of Substitution for group R_H is between 0.0005 and 0.1, more preferably between 0.005 and 0.05, and most preferably between 0.01 and 0.05;
- the Degree of Substitution for group R_C wherein Z is H or M is between 0.2 and 2.0, more preferably between 0.3 and 1.0, and most preferably between 0.4 and 0.7;
- if any R_H bears a positive charge, it is balanced by a suitable anion; and
- two R₄'s on the same nitrogen can together form a ring structure selected from the group consisting of piperidine and morpholine.

3. The detergent composition of any of claims 1-2, wherein the cyclic amine based polymers, oligomers or copolymers are of the general formula:




wherein;


each T is independently selected from the group consisting of H, C₁-C₁₂ alkyl, substituted alkyl,

C₇-C₁₂ alkylaryl,


-(CH₂)_hCOOM, -(CH₂)_hSO₃M, CH₂CH(OH)SO₃M, -(CH₂)_hOSO₃M,



-wherein W is characterized by at least one cyclic constituent selected from the group consisting of:



in addition to the at least one cyclic constituent, W may also comprise an aliphatic or substituted aliphatic moiety of the general structure;



-each B is independently C₁-C₁₂ alkylene, C₁-C₁₂ substituted alkylene, C₃-C₁₂ alkenylene, C₈-

C₁₂ dialkylarylene, C₈-C₁₂ dialkylarylenediyl, and -(R₅O)_nR₅-;


-each D is independently C₂-C₆ alkylene;

-each Q is independently selected from the group consisting of hydroxy, C₁-C₁₈ alkoxy, C₂-C₁₈ hydroxyalkoxy, amino, C₁-C₁₈ alkylamino, dialkylamino, trialkylamino groups, heterocyclic monoamino groups and diamino groups;


-each R₁ is independently selected from the group consisting of H, C₁-C₈ alkyl and C₁-C₈ hydroxyalkyl;

-each R₂ is independently selected from the group consisting of C₁-C₁₂ alkylene, C₁-C₁₂ alkenylene, -CH₂-CH(OR₁)-CH₂, C₈-C₁₂ alkarylene, C₄-C₁₂ dihydroxyalkylene, poly(C₂-C₄ alkyleneoxy)alkylene, H₂CH(OH)CH₂OR₂OCH₂CH(OH)CH₂-, and C₃-C₁₂ hydrocarbyl moieties;

provided that when R₂ is a C₃-C₁₂ hydrocarbyl moiety the hydrocarbyl moiety can comprise from about 2 to about 4 branching moieties of the general structure:



-each R₃ is independently selected from the group consisting of H, O, R₂, C₁-C₂₀ hydroxyalkyl, C₁-C₂₀ alkyl, substituted alkyl, C₆-C₁₁ aryl, substituted aryl, C₇-C₁₁ alkylaryl, C₁-C₂₀ aminoalkyl, -(CH₂)_hCOOM, -(CH₂)_hSO₃M, CH₂CH(OH)SO₃M, -(CH₂)_hOSO₃M,



-each R₄ is independently selected from the group consisting of H, C₁-C₂₂ alkyl, C₁-C₂₂ hydroxyalkyl, aryl and C₇-C₂₂ alkylaryl;

-each R₅ is independently selected from the group consisting of C₂-C₈ alkylene, C₂-C₈ alkyl substituted alkylene; and

A is a compatible monovalent or di or polyvalent anion;

M is a compatible cation;

b = number necessary to balance the charge;

each x is independently from 3 to 1000;

each c is independently 0 or 1;

each h is independently from 1 to 8;


each q is independently from 0 to 6;

each n is independently from 1 to 20;


each r is independently from 0 to 20; and

each t is independently from 0 to 1.


4. The detergent composition of any of claims 1-3, wherein each R₁ is H and at least one W is selected from the group consisting of:



5. The detergent composition of any of claims 1-4, wherein each R₁ is H and at least one W is selected from the group consisting of:



6. The detergent composition of any of claims 1-5, wherein each R_1 is H and at least one W is selected from the group consisting of:



7. The detergent composition of any of claims 1-6, wherein each R_H is independently selected from the group consisting of C_5 - C_{20} alkyl, C_5 - C_7 cycloalkyl, C_7 - C_{20} alkylaryl, C_7 - C_{20} arylalkyl, substituted alkyl, hydroxyalkyl, C_1 - C_{20} alkoxy-2-hydroxyalkyl, C_7 - C_{20} alkylaryloxy-2-hydroxyalkyl, $(R_4)_2$ N-alkyl, $(R_4)_2$ N-2-hydroxyalkyl, $(R_4)_3$ N-alkyl, $(R_4)_3$ N-2-hydroxyalkyl, and C_6 - C_{12} aryloxy-2-hydroxyalkyl.

8. A laundry additive composition characterized by:

- a) from 1% to 80% by weight of water; and
- b) from 0.01% to 5.0%, preferably from 0.1% to 4.0%, by weight of a mixture of cyclic amine based polymers, oligomers or copolymers and hydrophobically modified cellulosic based polymers or oligomers.

9. The detergent composition of any of claims 1-8, wherein the composition further is characterized by an inorganic peroxygen bleaching compound, which is preferably selected from the group consisting of alkali metal salts of perborate, percarbonate and mixtures thereof, and a bleach activator, which is preferably nonanoyloxybenzene sulfonate.

10. The detergent composition of any of claims 1-9, wherein the composition further is characterized by a cellulase enzyme.

DECLARATION COMBINED WITH POWER OF ATTORNEY

Page 1 of 2

Attorney Docket No. 7292

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled Laundry Detergent Compositions With A Combination Of Cyclic Amine Based Polymers And Hydrophobically Modified Carboxy Methyl Cellulose

the specification of which

(check ☐ is attached hereto.
 one) ☒ was filed on October 6, 1999 as United States Application No. or
 PCT International Application Serial No. PCT/US99/23146
 and was amended on _____
 (if applicable)

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37 Code of Federal Regulations §1.56.

I hereby claim foreign priority benefits under Title 35 United States Code §119(a)-(d) or §365(b) of any foreign application(s) for patent or inventor's certificate, or §365(a) of any PCT International application which designated at least one country other than the United States of America, listed below and have also identified below any foreign application for patent or inventor's certificate, or of any PCT international application having a filing date before that of the application on which priority is claimed:

Prior Foreign Application(s)Priority Claimed

(Number)

(Country)

(Day/Month/Year Filed)

Yes

No

I hereby claim the benefit under Title 35, United States Code §119(e) of any United States provisional application(s) listed below.

60/103,978October 13, 199860/148,053August 10, 1999

Application Serial No.

Filing Date

Application Serial No.

Filing Date

I hereby claim the benefit under Title 35 United States Code §120 of any United States application(s), or §365(c) of any PCT International application designating the United States of America, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of Title 35 United States Code §112, I acknowledge the duty to disclose information which is material to patentability as defined in Title 37 Code of Federal Regulations §1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application:

U.S. Parent Application Number	PCT Parent Number	Parent Filing Date (MM/DD/YYYY)	Parent Patent Number (If applicable)

As named inventor, I hereby appoint the following registered practitioner(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith:

<u>Atty Name</u>	<u>Atty Reg Number</u>	<u>of Attorney Attached</u>	
Kim William Zerby	<u>32,323</u>	<input type="checkbox"/> Yes	<input checked="" type="checkbox"/> No
Jacobus C. Rasser	<u>37,043</u>	<input type="checkbox"/> Yes	<input checked="" type="checkbox"/> No
T. David Reed	<u>32,931</u>	<input type="checkbox"/> Yes	<input checked="" type="checkbox"/> No
Timothy B. Guffey	<u>41,048</u>	<input type="checkbox"/> Yes	<input checked="" type="checkbox"/> No
Brian M. Bolam	<u>37,513</u>	<input type="checkbox"/> Yes	<input checked="" type="checkbox"/> No
Pankaj M. Khosla	<u>37,978</u>	<input type="checkbox"/> Yes	<input checked="" type="checkbox"/> No
D. Mitchell Goodrich	<u>42,592</u>	<input type="checkbox"/> Yes	<input checked="" type="checkbox"/> No
George W. Allen	<u>26,143</u>	<input type="checkbox"/> Yes	<input checked="" type="checkbox"/> No

SEND CORRESPONDENCE TO:

D. Mitchell Goodrich

The Procter & Gamble Company(513) 627-6250

Name

Phone No.

Ivorydale Technical Center, 5299 Spring Grove Avenue, Cincinnati, Ohio 45217

Street

City

State

Zip Code

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

100 Full name of sole or first joint inventor Rajan Keshav Panandiker

Inventor's signature Rajan Keshav Panandiker

Date 11/4/99

Residence 6484 Oregon Pass, West Chester, Ohio 45069 OH

Citizenship United States

Post Office Address The Procter & Gamble Company, Ivorydale Technical Center
5299 Spring Grove Avenue, Cincinnati, Ohio 45217

200 Full name of second joint inventor, if any Jennifer Ann Leupin

Inventor's signature Jennifer Ann Leupin

11/17/99
Date

Residence 9452 Hunters Creek Drive, Cincinnati, Ohio 45242 OH

Citizenship United States

Post Office Address The Procter & Gamble Company, Ivorydale Technical Center
5299 Spring Grove Avenue, Cincinnati, Ohio 45217

300 Full name of third joint inventor, if any William Conrad Wertz

Inventor's signature William Conrad Wertz

11/4/99
Date

Residence 1273 Morgan Road, West Harrison, Indiana 47060 IN

Citizenship United States

Post Office Address The Procter & Gamble Company, Ivorydale Technical Center
5299 Spring Grove Avenue, Cincinnati, Ohio 45217

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In the U.S. National Phase Entry
Under 35 USC 371 from
International Application of
PANANDIKER, Rajan Keshav et al.
Int'l. Application No. PCT/US99/23146
Filed in the RO/US on 06 October 1999
Entitled: *Laundry Detergent Compositions With A Combination
Of Cyclic Amine Based Polymers And Hydrophobically
Modified Carboxy Methyl Cellulose*

ASSOCIATE POWER OF ATTORNEY

Assistant Commissioner for Patents
Box PCT
Washington, D.C. 20231

Dear Sir:


You are requested to recognize K. W. Zerby (Registration No. 32,323), B. M. Bolam (Registration No. 37,513), F. C. Turner (Registration No. 39,863), C. B. Cook (Registration No. 39,151), M. Dressman (Registration No. 42,498), and R. S. Echler, Sr. (Registration No. 41,006) of The Procter & Gamble Company, Cincinnati, Ohio, as Associate Attorneys to prosecute this application, to make alterations and amendments therein, and to transact all business in the Patent Office connected with the application or with the patent granted thereupon.

Please address all future communications to:

M. Dressman, Patent Attorney
Customer Number 27751

Respectfully submitted for Applicants,

By



T. David Reed
Agent for Applicant
Registration No. 32,931

Cincinnati, Ohio
03 April 2001
(513) 627-7025/FAX 627-6333

105040 22230660

6